

#### General product description

The property profile of the unalloyed quenched and tempered steel C60 is optimized with maximum strength and toughness by the Xtreme Performance Technology. It is particularly suitable for components that require a combination of very high endurance and wear resistance under load.

#### International description

Steel number	EU/DE	ASTM	JIS	AFNOR	B.S.	SS
1.0601	C60	1060	S60CM	C60	C60 60CS/HS	C60

#### Chemical composition (cast analysis by mass-%)

Variant	C	Si	Mn	P	S	Cr	Mo	Ni	Cu
min.	0,57	0,10	0,60	–	–	–	–	–	–
max.	0,65	0,40	0,90	0,045	0,045	0,40	0,10	0,40	0,30

The analysis corresponds to C60 (1.0601) according to DIN EN ISO 683-1.  
Customer-specific chemical analyses are possible after consultation.

#### Mechanical-technological properties

Variant	R <sub>p0,2</sub> [MPa]	R <sub>m</sub> [MPa]	A <sub>5</sub> [%]	A <sub>g</sub> [%]	Z [%]	KV <sub>RT</sub> [J]	T <sub>27</sub> [°C]
high strength, high toughness	795	900	19	8	50	80	-40

Typical mechanical-technological properties:  
R<sub>p0,2</sub> = 0.2% yield strength, R<sub>m</sub> = tensile strength, A<sub>5</sub> = elongation at fracture,  
A<sub>g</sub> = uniform elongation, Z = reduction of area,  
KV = Charpy impact strength according to DIN EN ISO 148-1, RT = room temperature,  
T = temperature, T<sub>27</sub> = transition temperature of the Charpy impact strength at 27 J.

Customized mechanical properties are possible after consultation.

#### Carbon equivalent

Max. CET (CEV) 0,77 (0,87)

Typ. CET (CEV) 0,71 (0,78)

$$\text{CET} = \text{C} + \frac{\text{Mn} + \text{Mo}}{10} + \frac{\text{Cr} + \text{Cu}}{20} + \frac{\text{Ni}}{40}$$

$$\text{CEV} = \text{C} + \frac{\text{Mn}}{6} + \frac{\text{Cr} + \text{Mo} + \text{V}}{5} + \frac{\text{Cu} + \text{Ni}}{15}$$

#### Microstructure

The microstructure and the microscopic oxide purity grade according to DIN 50602 can be agreed upon. The grain size according to ASTM E 112 is  $\geq 10$ .

#### Surface properties

The surface condition complies with the requirements of SN EN 10277. The bars are crack-tested according to surface quality class 3 as standard. In the standard version, the ends of the bars up to 50 mm are not tested.

#### Miscellaneous

Other agreements according to order.

#### Condition of delivery

- Bar steel, XTP® treated
- Dimension range 18 - 40 mm
- Delivery length up to 8,000 mm
- Tolerance h11 and bar straightness 0.5 mm/m according to DIN EN 10278

#### Fabrication and other recommendations

Very good weldability, comparatively good machinability, thread rolling and cutting capability, very good cold formability, bendable.

#### Your benefits at a glance

##### Increased fatigue strength

- Higher load capacity and component safety
- Longer service life and lower maintenance costs
- Lightweight potential

##### Increased productivity

- Reduced hardness distortion and increased straightness
- Optimized diameter tolerances

##### Highest quality

- Single bar processing
- State-of-the-art process control
- Low decarburization and scale formation

For further info on our product range of tool steel, stainless steel and Engineering steel please visit [www.swisssteelgroup.com](http://www.swisssteelgroup.com)

Discover our Green Steel portfolio on [www.swissgreensteel.com](http://www.swissgreensteel.com)

The information and data contained in this document represent standard or average values and do not constitute a warranty or guarantee of minimum or maximum values. The information contained in our material test certificates is solely authoritative. Application recommendations for the materials described in this document are provided for guidance only to enable the reader to make their own decisions and do not constitute an express or implied warranty or guarantee that a material is suitable for a particular application.

Subject to change, errors and printing mistakes. The desired performance characteristics are only binding if they are exclusively agreed upon at the time of contract conclusion.

30.06.23 Rev. N°1

**Swiss Steel Group**  
Steeltec AG / Steeltec GmbH:  
Düsseldorf  
[info.engineering@swisssteelgroup.com](mailto:info.engineering@swisssteelgroup.com)