

#### General product description

The compensation steel 42CrMo(S)4 can be adjusted to individual processing and component requirements using Xtreme Performance Technology. The 42CrMo(S)4 XTP® is suitable for components that are subjected to the highest mechanical loads.

#### International description

Steel number	EU/DE	ASTM	JIS	AFNOR	B.S.	AISI
					708M40 709M40 708A42 708H37	
1.7225	42CrMo4	A331 A505	SCM4 SCM4H	40CD4 42CD4	EN19 EN19A	
1.7727	42CrMoS4	A519 A640	SCM440 SCM440H	40CD4u 42CD4u	EN19B EN19C	4137 4140

#### Chemical composition (cast analysis in percentage by mass)

Element	C	Si	Mn	P	S	Cr	Mo
min.	0,38	0,10	0,60	–	0,020 / –	0,90	0,15
max.	0,45	0,40	0,90	0,025	0,040 / 0,035	1,20	0,30

The analysis corresponds to 42CrMoS4 / 42CrMo4 (1.7227 / 1.7225) according to DIN EN ISO 683-2. Customized chemical analyses are possible upon consultation.

#### Mechanical-technological properties

Strength class	R <sub>p0,2</sub> [MPa]	R <sub>m</sub> [MPa]	A <sub>5</sub> [%]	Z [%]	KV <sub>RT</sub> [J]	T <sub>27</sub>
1	>850	1000–1200	≥14	≥55	≥70	-50
2	>1050	1200–1400	≥11	≥50	≥45	-20
3	>1250	1400–1600	≥10	≥45	≥15	
4	>1450	1600–1800	≥ 8	≥40	≥10	

Typical mechanical-technological properties:  
R<sub>p0,2</sub> = 0.2% yield strength, R<sub>m</sub> = tensile strength, A<sub>5</sub> = elongation at fracture,  
A<sub>5</sub> = uniform elongation, Z = reduction of area,  
KV = Charpy impact strength according to DIN EN ISO 148-1, RT = room temperature,  
T = temperature, T<sub>27</sub> = transition temperature of the Charpy impact strength at 27 J.

#### Dynamic properties

42CrMo4 XTP®	Bending fatigue strength σ <sub>bw</sub> [MPa]	Tensile strength R <sub>m</sub> [MPa]
Ø 32 mm	697	1587

Smooth samples from the core

#### Carbon equivalent

Max. CET (CEV)	0,64 (0,93)
Typ. CET (CEV)	0,58 (0,83)

$$\text{CET} = \text{C} + \frac{\text{Mn} + \text{Mo}}{10} + \frac{\text{Cr} + \text{Cu}}{20} + \frac{\text{Ni}}{40}$$

$$\text{CEV} = \text{C} + \frac{\text{Mn}}{6} + \frac{\text{Cr} + \text{Mo} + \text{V}}{5} + \frac{\text{Cu} + \text{Ni}}{15}$$

#### Microstructure

Minimum 90% quenched and tempered microstructure for the grade 42CrMo(S)4 +HH. Surface hardness minimum 53 HRC according to DIN EN ISO 683-2. The microscopic oxidic purity grade according to DIN 50602 can be agreed upon. The grain size according to ASTM E 112 is  $\geq 9$ .

#### Surface properties

The surface condition complies with the requirements of SN EN 10277. The bars are crack-tested according to surface quality class 3 as standard. In the standard version, the ends of the bars up to 50 mm are not tested.

#### Miscellaneous

Other agreements according to order.

#### Condition of delivery

- Round bars, XTP®-treated
- Dimension range 18 - 40 mm
- Delivery lengths up to 8,000 mm
- Tolerance h11 and bar straightness 0.5 mm/m according to DIN EN 10278

#### Fabrication and other recommendations

- Comparatively good machinability
- Bendable
- Thread rolling and cutting possible

#### Your benefits at a glance

##### Increased durability

- Higher load capacity and component safety
- Longer service life and lower maintenance costs
- Potential for lightweight construction

##### Increased productivity

- Reduced distortion and increased straightness
- Optimized diameter tolerance

##### Highest quality

- Single bar processing
- State-of-the-art process control
- Low decarburization and low scale formation

For further info on our product range of tool steel, stainless steel and Engineering steel please visit [www.swisssteelgroup.com](http://www.swisssteelgroup.com)

30.06.23 Rev. N°1

Discover our Green Steel portfolio on [www.swissgreensteel.com](http://www.swissgreensteel.com)

The information and data contained in this document represent standard or average values and do not constitute a warranty or guarantee of minimum or maximum values. The information contained in our material test certificates is solely authoritative. Application recommendations for the materials described in this document are provided for guidance only to enable the reader to make their own decisions and do not constitute an express or implied warranty or guarantee that a material is suitable for a particular application.

Subject to change, errors and printing mistakes. The desired performance characteristics are only binding if they are exclusively agreed upon at the time of contract conclusion.

**Swiss Steel Group**  
Steeltec AG / Steeltec GmbH:  
Düsseldorf  
[info.engineering@swisssteelgroup.com](mailto:info.engineering@swisssteelgroup.com)